

# **CEILING ULTRA**



### **TECHNICAL DATA SHEET**

### **PRODUCT DESCRIPTION**

Water based, acrylic resin based, high hiding power and whiteness, non-splash, plastic ceiling paint.

### **FEATURES**

- Deep Matt
- Smooth appearance
- Odorless
- Allows surface to breath
- High hiding power
- High whiteness
- Easy application
- Not leave brush marks
- Non-splash
- · Not cause cracks, distention and flaking

### **RECOMMENDED FOR**

Any kind of plaster, dry wall or lime surface

### **SURFACE PREPARATION**

Throughly remove dirt, dust and bubbled or flaking paint.

## **APPLICATION**

Applied in two coats. 2-3 hours should be allowed between coats.

In airless applications, after 35% thinning, application can be made between 150-200 bars with the recommended nozzle.

# **Application Features**

Thinning Ratio 20-30 % with water (by volume)

Application Temperature (°C) 5-30

Coverage (m<sup>2</sup>/L) 8-10 (per coat) Coverage (m<sup>2</sup>/kg) 5-7 (per coat)

# **Application Equipment**

Brush Apply with top quality brush.
Roller Apply with high quality roller.

Spray gun with 150-200 bar; nozzle: should be 0.013-0.019 in.

Polisan Kansai Boya San. ve Tic. A.Ş. Headquarters/Factory: Demirciler osb. mah. Refik Baydur cd. No:7/3 Dilovası/KOCAELİ Phone: +90 (0262) 679 71 00 www.polisankansai.com

Revision No: 06

Publish Date : 15.10.2024

Sample Text



# **CEILING ULTRA**



#### **TECHNICAL DATA SHEET**

## **TECHNICAL SPECIFICATIONS**

Drying Time (20 °C)

Recoat (h) 2-3 Full dry (h) 1-3

#### **TS Classification**

It confirms with TS 5808 and certificated TSE standart.

Poz No

### STORAGE and PACKAGING

Packaging Information

1 KG, 3.5 KG, 10 KG, 17.5 KG

Storage Conditions

It should be stored in a closed container without being exposed to direct sunlight. The ambient temperature while storage should be between 5-35  $^{\circ}$ C. Keep container closed when not in use.

Preserve against freezing.

#### **HEALTH AND SAFETY INFORMATION**

Refer to the instructions specified in the harmfulness and precautionary statements on the product packaging. Product of the safety data sheet should be treated by the rules. Refer to the nearest health facility for unexpected health problems.

# **LEGAL NOTES**

All the information and guidelines given in this technical bulletin was formed and developed through the experience in the laboratories of PB, and was systematically collected by our field engineers. "Polisan Kansai Boya"has the right to make changes in the product where necessary, without notice. The information given above is valid for the product from the date of publication. It is the user's responsibility to verify the accuracy of the information. The product should be used based on the technical information form for the recommended purpose. It is the responsibility of the users to implement all measures for the fulfilment of the specified requirements. The data in the technical information form is designed to give descriptions of the product performance, under specific test conditions. An important factor in product performance is the variables that may occur in the initial process which should be used as a general guide to the user. Any unauthorised use of this product not covered in the written guidelines, PB will not be held legally responsible. It is always the responsibility of the user to take all necessary precautions regarding specific requirements of the law set out in local and national legislation. Follow the rules of the safety information provided in the Safety Data Sheet regarding operating procedure of the product, protective equipment, storage, fire and first aid etc. Conditions regarding the use of this product after its end date has no warranty. We can not accept responsibility for products past their expiry date. Responsibility can not be accepted.

Please contact the Technical Service department for more detailed information about the product.

Revision No: 06

Publish Date : 15.10.2024

Sample Text

<sup>\*</sup> The specified drying time; temperature, humidity, such media may vary depending on the application thickness and application conditions.